

Note on English translation / Hinweise zur englischen Fassung

This is a translation of the product data sheet valid in Germany.

All stated details and properties are in compliance with the regulations of the German standards and building regulations. They are only applicable for the specified products, system components, application rules, and construction details in connection with the specifications of the respective certificates and approvals.

Knauf Gips KG denies any liability for applications outside of Germany as this requires changes acc. to the respective national standards and building regulations.



Drywall Systems

K714F.de

Product Data Sheet

2020-10



Fire-Resistant Board GKFI

Impregnated Gypsum Board for Fire Protection Systems in Drywall Construction

Product description

Fire-resistant boards GKFI are gypsum boards with a fibre-reinforced gypsum core for fire resistant systems. The gypsum boards are impregnated for reduced water absorption in rooms with moderately high humidity.

- | | |
|-------------------------|-------|
| ■ Board type | |
| DIN 18180 | GKFI |
| EN 520 | DFH2 |
| ■ Colour of board liner | |
| Face side | green |
| Rear side | grey |
| ■ Rear side marking | red |

Storage

Store boards on board pallets in a dry environment.

Quality

In compliance with EN 520, the product is subject to initial type testing and continuous factory production control and bears the CE marking.

Properties and added value

- Impregnated for reduced water absorption
- Good coherence of structure when exposed to fire
- Easy application
- Non-combustible
- Low expansion and shrinkage when climate conditions change

Field of application

Fire-resistant board GKFI is used in all fields of interior works as cost-effective cladding for drywall systems in rooms with fire resistance requirements and moderately high humidity.

Rooms with moderately high humidity are rooms with a constant relative air humidity of $\leq 70\%$ (e.g. domestic bathrooms).

In addition, DIN EN 1995-1-1NA allows the application in structural wood frame wall panels as exterior cladding in the service class 2 (e.g. as substrate for ETICS).

Suitable for the following systems:

- Ceiling linings and suspended ceilings
- Attic linings
- Metal stud partitions
- Wood frame partitions
- Structural wood frame wall panels
- Installation shaft walls

Technical data

Description	Standard	Unit	Fire-ResistantBoardGKFI
Board type Germany	DIN 18180	–	GKFI
Board type European	EN 520	–	DFH2
Reaction to fire EN 13501-1	EN 520	Class	A2-s1, d0 (B)
Width dimensional tolerance	EN 520	mm	+0 / -4
Length dimensional tolerance	EN 520	mm	+0 / -5
Thickness dimensional tolerance	EN 520	mm	+0.5 / -0.5
Angularity dimensional tolerance	EN 520	mm per board width	≤ 2.5
Thermal conductivity λ	EN ISO 10456	W/(m·K)	0.23
Water vapour resistance factor μ dry	EN ISO 10456	–	10
Water vapour resistance factor μ wet	EN ISO 10456	–	4
Shrinkage and expansion air humidity per 1 % change of relative air humidity	–	mm/m	0.005 / 0.008
Shrinkage and expansion temperature per 1 Kelvin change of temperature	–	mm/m	0.013 / 0.02
Long term temperature exposure (max. limit)	–	°C	≤ 50
Density	–	kg/m ³	≥ 800
Board weight	DIN 18180	kg/m ²	≥ 12
Flexural breaking load longitudinal direction	DIN 18180	N	≥ 735
Flexural breaking load transverse direction	DIN 18180	N	≥ 250
Characteristic compressive strength $f_{c,90,k}$ (out of plane board)	DIN EN 1995/1/1 NA	N/mm ²	≥ 5.5
Characteristic bending tensile strength $f_{m,k}$ (out of plane loads) longitudinal direction	DIN EN 1995/1/1 NA	N/mm ²	≥ 5.4
Characteristic bending tensile strength $f_{m,k}$ (out of plane loads) transverse direction	DIN EN 1995/1/1 NA	N/mm ²	≥ 1.8
Mean E modulus E_{mean} (for out of plane loads) longitudinal direction	EN 1995/1/1 NA	N/mm ²	≥ 2800
Mean E modulus E_{mean} (for out of plane loads) transverse direction	EN 1995/1/1 NA	N/mm ²	≥ 2200
Total water absorption	EN 520	%	≤ 10

Application

Note	Application should be undertaken in accordance to the applicable standards and acc. to the relevant Knauf system data sheets for drywall systems.

Product range

Description	Width mm	Length mm	Thick- ness mm	Edges	Delivery weight kg/m ²	Packaging unit	Material number	EAN
Fire-Resistant Board GKFI 15	1250	2000	15	HRAK SFK	12.5	40 pieces / pallet 100 m ² / pallet	00002918	4003982001719
		Customized length		HRAK SSK		–	00007490	9002943031623

HRAK = Half-rounded tapered long edge

SFK = Bevelled cut edge

SSK = Front cut square edge

Sustainability and environment

Short description	Unit	Value
Requirements of the German AgBB-scheme	–	fulfilled
Complies with the requirements of the French emission class	–	A+
Environmental product declaration	–	EPD-KNA-20160144-IAG1-DE



Observe safety data sheet!

For safety data sheets and CE marking see
pd.knauf.de



Videos for Knauf systems and products can be found under the following link:

www.youtube.com/knauf



The iPad App Knauf Infothek now provides all the current information and documents from Knauf Gips KG at any time and in every location in a clear and comfortable way.

[Knauf Infothek](#)

Knauf Direct

Technical Advisory Service:

▶ knauf-direkt@knauf.de

▶ www.knauf.de

Knauf Gips KG Am Bahnhof 7, 97346 Iphofen, Germany

All technical changes reserved. Only the current printed instructions are valid. The stated information represents current state-of-the-art Knauf technology. The entire state of approved engineering rules, appropriate standards, guidelines, and rules of craftsmanship are not included herewith. These and all application instructions have to be adhered to separately by the installer. Our warranty is expressly limited to our products in flawless condition. All application quantities and delivery amounts are based on empirical data that are not easily transferable to other deviating areas.

All rights reserved. All amendments, reprints and photocopies, including those of excerpts, require our expressed permission.