

Note on English translation / Hinweise zur englischen Fassung

This is a translation of the product data sheet valid in Germany.

All stated details and properties are in compliance with the regulations of the German standards and building regulations. They are only applicable for the specified products, system components, application rules, and construction details in connection with the specifications of the respective certificates and approvals.

Knauf Gips KG denies any liability for applications outside of Germany as this requires changes acc. to the respective national standards and building regulations.

KNAUF

Plaster & Façade Systems

P222.de

Product Data Sheet

2023-09



Universal-Feinspachtel SPRINT finishing compound

Rapidly workable cementitious finishing compound

Product description

Rapidly workable finishing compound for use on almost all substrates without pretreatment of the substrate for use in interiors and exteriors. Due to the surface application, from almost zero to 5 mm, in some areas up to 50 mm, universal application in interiors and exteriors is possible.

As a system component of the SPRINT technology (rapidly reworkable), when applied in thin layers in interiors, subsequent coating with Raumklima products can be applied after approx. 4 to 5 hours. When used as a thin-layer plaster in exteriors, NOBLO 600 SPRINT or MineralAktiv Fassadenfarbe paint can be applied as a subsequent coat on the following day.

Composition

White cement, limestone powder, water-retaining additives, bonding agents and mortar additives.

Storage

Store the bags on wooden pallets in a dry environment. The product can be stored for at least 6 months.

Re-bag damaged bags and use first.

Quality

In compliance with EN 998-1, the product is subject to initial type testing and continuous factory production control and bears the CE marking.

Properties and added value

- General-purpose rendering/plastering mortar GP acc. to EN 998-1
- Compressive strength category CS IV acc. to EN 998-1
- Following layers without the generally standard drying times
- Can be smoothed and sanded
- With integrated SPRINT TECHNOLOGY
- Biocide-free
- For interior and exterior application
- For the façade and plinth areas
- Manual application
- Natural white



www.emicode.com/en

Field of application

Creation of smoothed surfaces in all interior rooms of water action classifications W0-I to W3-I acc. to DIN 18534 as well as levelled thin-layer plaster for subsequent following layers. As a thin-layer plaster in exteriors on the plinth and façade surface. Particularly suitable when rapid continuation of the building phase is required.

- On all mineral basecoats and finishing coats
- On all dispersion-based top coats and paints
- Filling of cracks, breaks in the masonry, slots and joints
- Can be smoothed and sanded
- Reworking of tiles and as a substrate for tiles

Application

Substrate and pretreatment

Substrate	Pretreatment
SM600 SPRINT	None
Lime, lime-cement and cementitious basecoats	None
Reinforcement plaster	None
Stable paint coats, old render	None
Stable tiles	Quarzgrund Pro / Raumklima Grundierung primer ¹⁾
Masonry	Isogrund
Restoration plasters	None
Gypsum and gypsum lime plasters	Quarzgrund Pro / Raumklima Grundierung primer ¹⁾
Prefabricated concrete units	None
Smooth concrete, prefabricated concrete units	Quarzgrund Pro / Raumklima Grundierung primer ¹⁾
Wallboard	Pretreat surfaces with Grundol if required. Pretreatment with Aton Sperrgrund barrier coating.
Plaster blocks	Quarzgrund Pro / Raumklima Grundierung primer ¹⁾

Allow primer coats to dry for at least 12 hours before continuing work.

1) Drying time until subsequent application of Quarzgrund Pro/Raumklima Grundierung primer approx. 2 hours.

Preparation

Check substrate for compliance with VOB part C, DIN 18350, DIN 18345 chapter 3.1 and/or according to VOB part B, DIN 1961 paragraph 4 no. 3. Clean the substrate of dust and remove loose parts, ensure that the surface is smooth. Cover easily-soiled building components before commencement in accordance with Code of Practice "Ablebe- und Abdekarbeiten für Maler- und Stuckateurarbeiten" (German only) issued by the German Bundesverband Ausbau und Fassade. Protect weather-exposed surfaces from precipitation and direct sunlight.

All substrates must be stable, dry, even and free of grease and dust as well as free of any residual substances that may reduce the adhesion.

Mixing

Mixing by hand

Thoroughly mix the content of one bag with 7.2 to 8.0 litres of clean water (depending of the application) without further additions until an application-ready lump-free consistence is achieved. After a maturing time of 2 to 3 minutes, it must be stirred again.

Application

After stirring, spread and level with a stainless steel tool. The working time is approx. 45 minutes.

In interiors apply and level Universal-Feinspachtel SPRINT finishing compound up to a maximum of 5 mm per work step. When initial setting has commenced, rule with a feather edge / wide spatula. Depending on the surface quality, the surface can be subsequently re-worked or smoothed again with a wide spatula. Universal-Feinspachtel finishing compound can be skimmed to almost layer thickness zero.

Slots, break-outs, recesses, joints etc. should be filled and sealed with Universal-Feinspachtel SPRINT finishing compound in a corresponding stiff consistence (depending on the application thickness) before the surface is worked. After a drying time of approx. 2 to 3 hours, the entire surface can be worked with Universal Feinspachtel SPRINT finishing compound.

In case of layer thicknesses up to 5 mm, the following layer can be applied after about 4 to 5 hours using optimally matched Raumklima products. In case of layer thicknesses > 5 mm the following layer can be applied on the following day.

In exteriors, apply Universal Feinspachtel SPRINT finishing compound on stable old plasters / coating of thin-layer plaster in a layer thickness of about 3 mm and rule flush. After initial setting has commenced, rule with a feather edge / wide spatula. Depending on the surface quality, the surface can be subsequently re-worked or smoothed again with a wide spatula. In areas at risk of cracking, a reinforcing mesh 4x4 or 5x5 mm must be embedded in the centre of the fresh mortar. Crack-free, stable old finishing plasters / coats where no mesh reinforcement is necessary can be reworked with texture filling (grain covering).

Reinforcement

In case of a change of materials in the plaster substrate, at locations where there is a risk of cracking, where XPS-R insulation boards are installed on a small surface, wood wool lightweight boards, different plaster thicknesses and expected stresses from the basecoat etc., embed reinforcing mesh 4x4 or 5x5 with at least 100 mm joint overlap and 200 mm overlap on all sides to the flanking component in the middle of the finishing compound.

If a painter's fleece is used in interiors, ensure that skips/flaws do not occur. Embed the fleece layer directly after application of Universal Feinspachtel SPRINT finishing compound. Embed the fleece layer on the entire surface e.g. embed well with a plastic trowel or surface leveller. The layer thickness under the fleece layer may not be less than 1 mm after the fleece is pressed in.

Plinth application

The render system must be protected against the ingress of moisture at the connection to the lower edge. The required plaster sealing or the necessary moisture protection must be applied up to at least 5 cm above the edge of the ground line or top edge of the covering. In the lower edge, this is recommended for application up to the existing building sealing. As a plaster seal / moisture protection, apply Socket-Dicht in a layer thickness of at least 1.2 mm (dry layer thickness min. 1 mm). A protective layer with slip membrane (e.g. fleece laminated dimpled sheet) should be provided on the construction as protection against damage after drying.

Substrate for tiling

Suitable as a substrate for tiles and floor slabs, if the weight of the tiles and floor slabs including the thin-bed mortar does not exceed 25 kg/m² and the layer thickness is at least 2 mm. Before application of the tile covering, allow to fully dry and harden for at least 3 days. Use a quick setting Flex-Fliesenkleber tile adhesive.

Application with water action classes W0-I to W3-I in accordance with DIN 18534. The waterproofing layer required acc. to DIN 18534 should be matched to the basecoat. We recommend Knauf Sockel-Dicht.

Application temperature / climatic conditions

Do not apply with air, component and/or substrate temperatures below +5 °C and ensure that the temperature does not fall below this temperature until the plaster has hardened sufficiently. Furthermore, the temperature should not exceed 30 °C during application.

In order to prevent rapid dehumidification of the fresh plaster by the exposure to direct sunshine (high surface temperatures), and/or strong wind (danger of cracks, reduction in strength) suitable protection measures / treatment (e.g. protective nets, keeping moist) are required.

Cleaning

Clean the machines and tools with water immediately after use.

Notes	<p>Renders must be applied according to EN 13914, DIN 18550, DIN 55699, DIN 18345 and DIN 18350 well as the generally recognized building engineering rules and valid guidelines.</p> <p>When applied as a top coat in combination with a protective paint system, protection against algal and fungal growth with an inhibiting effect can be achieved. No guarantee can, however, be given for long-term protection against algal and fungal growth. The susceptibility depends on the local and environmental conditions.</p> <p>Heating in rooms should only be put into operation in stages. Rapid dehumidification, e.g. using dehumidifiers should be avoided.</p>
--------------	---

Coatings and linings

Paints

In interiors, after approx 4 to 5 hours (haptic test) the following coating using Raumklima products can be undertaken. The maximum layer thickness should not exceed 5 mm. In case of larger layer thicknesses further coating is undertaken on the following day. When Raumklima Farbe E.L.F. Paint is used, the surfaces are pre-treated with Knauf Tiefengrund/Grundol, when using Raumklima Scheibenputz floted render / spray plaster with the quick drying Raumklima Grundierung primer.

On exteriors, NOBLO 600 SPRINT can be applied in a system with MineralAktiv Fassadenfarbe paint. In case of a subsequent coating on the following day, a maximum layer thickness of 3 mm should not be exceeded.

Caution	<p>In case of usage as a smooth plaster, a second coat with MineralAktiv Fassadenfarbe paint is obligatory.</p> <p>In case of subsequent coating of Universal Feinspachtel SPRINT finishing compound with other material than Raumklima paint coats, Raumklima finish coat, NOBLO 600 SPRINT and MineralAktiv Fassadenfarbe paint, the normal drying times must be observed.</p>
----------------	--

Technical data

Description	Standard	Unit	Universal-Feinspachtel SPRINT
Reaction to fire	EN 13501-1	Category	A1
Compressive strength	EN 1015--11	Category	CS IV
Water vapour diffusion resistance μ	EN 1015-19	–	≤ 20
Thermal conductivity $\lambda_{10, \text{dry, mat}}$ at P = 50 %	EN 1745	W/(m·K)	≤ 0.82
P = 90 %		W/(m·K)	≤ 0.89
Capillary water absorption	EN 1015-18	Category	$W_c 2$

The stated technical data were evaluated acc. to the respective test standards. Deviations under site conditions are possible.

Material requirement and efficiency

Application	Coat thickness mm	Consumption approx. kg/m ²	Yield approx. m ² /bag
Universal-Feinspachtel SPRINT	1	1.1	18
	3	3.3	6
	5	5.5	4

The consumption values were determined under laboratory conditions. Additional consumption resulting from conditions in practice must be taken into account. The material consumption depends on the roughness, evenness and absorption properties of the substrate as well as the machinery used.

Product range

Description	Application	Packaging unit	Material number	EAN
Universal-Feinspachtel SPRINT	20 kg	42 bags/pallet	00739551	4003950144622

Sustainability and environment

Short description	Unit	Value
Requirements of the German AgBB-scheme	–	fulfilled
Complies with the requirements of the French emission class	–	A+
Certificates	–	EC1 ^{PLUS} (acc. to GEV)



Observe safety data sheet!

For safety data sheets and CE marking see pd.knauf.de



Videos for Knauf systems and products can be found under the following link:
youtube.com/knauf



The Knauf Infothek App now provides all the current information and documents from Knauf Gips KG at any time and in every location in a clear and comfortable way.

knauf.de/infothek

Knauf Direct

Technical Advisory Service:

▶ knauf-direkt@knauf.com

▶ www.knauf.de

Knauf Gips KG Am Bahnhof 7, 97346 Iphofen, Germany

All technical changes reserved. Only the current printed instructions are valid. The stated information represents current state-of-the-art Knauf technology. The entire state of approved engineering rules, appropriate standards, guidelines, and rules of craftsmanship are not included herewith. These and all application instructions have to be adhered to separately by the installer. Our warranty is expressly limited to our products in flawless condition. All application quantities and delivery amounts are based on empirical data that are not easily transferable to other deviating areas.

All rights reserved. All amendments, reprints and photocopies, including those of excerpts, require our expressed permission.