




KNAUFCEILING
Solutions































TEHNIČKI LIST

Antaris



- Antaris je bela laminirana mineralna ploča u klasi A apsorpcije zvuka. Antaris je plafon kojim se dobija protivpožarnost i higijensko rešenje.
- Odlična zvučna apsorpcija (0.90 α_w)

- Visoka vrednost refleksije svetlosti (86%)
- ISO 5
- Idealno rešenje za maloprodajne objekte, kancelarije i sale za sastanke, tehničke prostorije i proizvodne objekte.

Detalji ivica Ostale dimenzije i ivice na upit		Board 	Tegular 24/90 	Tegular 15/90 															
Debljina (mm)		15	15	15															
Dimenzije (mm) Ostali formati na upit		600 x 600 675 x 675 1200 x 600	600 x 600 675 x 675 1200 x 600	600 x 600 675 x 675 1200 x 600															
Sistem		Vidljiva konstrukcija, demontažni - sistem C																	
Težina		2.9 kg / m ²																	
Boja		 Bela																	
Apsorpcija zvuka		EN ISO 354 $\alpha_w = 0.90$ prema EN ISO 11654 - Klasa A <table border="1"> <tr> <td>Frekvencija f (Hz)</td> <td>125</td> <td>250</td> <td>500</td> <td>1000</td> <td>2000</td> <td>4000</td> </tr> <tr> <td>α_p</td> <td>0.50</td> <td>0.80</td> <td>0.85</td> <td>0.85</td> <td>1.00</td> <td>1.00</td> </tr> </table> NRC = 0.90 prema ASTM C 423				Frekvencija f (Hz)	125	250	500	1000	2000	4000	α_p	0.50	0.80	0.85	0.85	1.00	1.00
Frekvencija f (Hz)	125	250	500	1000	2000	4000													
α_p	0.50	0.80	0.85	0.85	1.00	1.00													
Uzdužna zvučna izolacija		EN ISO 10848-2 $D_{n,f,w} = 28$ dB prema EN ISO 717-1 CAC = 29 dB prema ASTM E 413-10																	
Zvučna izolacija		EN ISO 10140-2 $R_w = 13$ dB prema EN ISO 717-1																	
Reakcija na požar		Euroclass A2-s1, d0 prema EN 13501-1 Klasa A prema ASTM E 84																	
Refleksija svetlosti		86%																	
Toplotna provodljivost		$\lambda = 0.040$ W/mk prema EN 12667																	
Otpornost na vlagu		95% RH																	
Klasa čistoće prostora		ISO 5 prema EN ISO 14644-1																	
Kvalitet vazduha		 A+	 E1																
Čišćenje																			
Održavanje		 43%	 EN ISO 14025	 EC 1272/2008 Annex G	 M1+														
		 www.blauer-engel.de/uz132																	

Proizvodi se mogu razlikovati od države do države. Molimo kontaktirajte svog lokalnog prodajnog predstavnika. Za dodatne i pravne informacije posetite našu web stranicu.