

Note on English translation / Hinweise zur englischen Fassung

This is a translation of the product data sheet valid in Germany.

All stated details and properties are in compliance with the regulations of the German standards and building regulations. They are only applicable for the specified products, system components, application rules, and construction details in connection with the specifications of the respective certificates and approvals.

Knauf Gips KG denies any liability for applications outside of Germany as this requires changes acc. to the respective national standards and building regulations.



Plaster & Façade Systems

P561.de

Product Data Sheet

2023-03



Noblo

Floated render with marble grains

Product description

Mineral finishing render with brilliant white marble grains for fine or subtle-elegant floated render, scratch render or grain-on-grain texture. A diverse range of textures can be achieved by use of various tools.

Composition

Hydrated lime, white cement, graded marble grains, water-retaining and water-repellent additives, and lightfast and alkaline resistant mineral colour pigments, if required.

Storage

Store the bags on wooden pallets in a dry environment. The product can be stored for at least 12 months. Re-bag damaged bags and use first.

Quality

In compliance with EN 998-1, the product is subject to initial type testing and continuous factory production control and bears the CE marking. Furthermore, the product is subject to external monitoring as a final layer in WARM WALL systems.

Properties and added value

- Coloured rendering mortar CR acc. to EN 998-1
- Compressive strength category CS II acc. to EN 998-1
- Biocide-free
- For interior and exterior application
- Water-repellent
- Application in the plinth area
- For machine or hand application
- Grain size 1.5, 2.0 and 3.0 mm
- White (approx. RAL 9003)
- Can be coloured subject to limitations in colour shades for mineral-based finishing coats compliant to the Knauf ColorConcept colour-shade selector card

Field of application

As a mineral finishing coat:

- On Knauf WARM WALL systems
- On lime, lime-cement and cementitious basecoats or reinforcement plaster
- On gypsum plasters
- On gypsum boards and plaster block

Application

Substrate and pretreatment

Substrate	Pretreatment
Lime, lime-cement and cementitious basecoats	Use Isogrund if required
Reinforcement plaster	Use Isogrund if required
Restoration plasters	None
Gypsum and gypsum lime plasters	Prime with Quarzgrund Pro/ Raumklima Grundierung ¹⁾
Smooth concrete, prefabricated concrete units	Prime with Quarzgrund Pro/ Raumklima Grundierung ¹⁾
Gypsum boards	Remove the dust and treat the sanded surfaces with Grundol if necessary. Pretreatment with Aton Sperrgrund barrier coating.
Plaster blocks	With absorbent substrates apply a primer coat of Grundol and a coat of Quarzgrund Pro / Raumklima Grundierung primer ¹⁾

Allow primer coats to dry for at least 12 hours before continuing work.

1) Drying time until subsequent application of Quarzgrund Pro/Raumklima Grundierung primer approx. 2 hours.

Preparation

Check substrate for compliance with VOB part C, DIN 18350, DIN 18345 chapter 3.1 and/or according to VOB part B, DIN 1961 paragraph 4 no. 3. Clean the substrate of dust and loose parts and remove, ensure that the surface is smooth. Cover easily-soiled building components before commencement in accordance with Code of Practice "Abklebe- und Abdekarbeiten für Maler- und Stuckateurarbeiten" (German only) issued by the German Bundesverband Ausbau und Fassade. Protect weather-exposed surfaces from precipitation and direct sunlight.

All substrates must be stable, dry, even and free of grease and dust as well as free of any residual substances that may reduce the adhesion.

Machines / equipment

Knauf PFT mixing pump G 4

- Stator D4-3
- Rotor D4-3
- Mortar hoses Ø 25 mm
- Wet mortar pumping distance up to 30 m

Mixing

Mixing by hand

Thoroughly mix the content of one bag with 7.5 litres of clean water without further additions until an application-ready lump-free consistence is achieved.

Mixing by machine

For machine application using mixing pumps, e.g. PFT G4, set the desired consistence by adding water. Prelubricate the hoses with wallpaper paste and fill them successively.

Application

Apply mortar in grain thickness to the full surface with a suitable stainless steel tool. In case of application by machine, spray on a thin layer of material and rule with a suitable stainless steel tool. Texture uniformly or model using a PVC trowel, foam rubber disc or polystyrene disc float.

Work fresh-in-fresh, do not re-smoothen surfaces already smoothened.

Always complete visually unified surfaces in one working step on the same day. Do not use a range of different tools to avoid differences in the colour and textural effects. Work simultaneously at all scaffolding levels with offset scaffolding levels.

Reinforcement

To minimize the occurrence of plaster cracking with lightweight plasters in exteriors, a reinforcement plaster with full-surface mesh insert on the basecoat is recommended. For exterior plaster surfaces where the plaster system is exposed to increased stress, e.g. special exposure of the façade, use of freely textured, brushed or sponged finishing plasters, finishing plasters < 2 mm grain size (acc. to DIN 18350, VOB Part C, < 3 mm), luminosity < 20, a reinforcing plaster with full-surface mesh insert is generally recommended. Refer to the "Leitlinie für das Verputzen von Mauerwerk und Beton - Guidelines for plastering masonry and concrete" issued by the VDPM e. V. (German only).

The exceptions to this case are Gigamit and Sockel Gigamit with a full surface mesh insert. For WARM WALL systems using Noblo 1.5 mm, apply an additional full surface embedded mesh in the basecoat. A basecoat layer of thickness of approx. 2 mm should be between the individual mesh layers.

Plinth application

The render system must be protected against the ingress of moisture at the connection to the lower edge. The required plaster sealing or the necessary moisture protection must be applied up to at least 5 cm above the edge of the ground line or top edge of the covering. In the lower edge, this is recommended for application up to the existing building sealing. As a plaster seal / moisture protection, apply Sockel-Dicht in a layer thickness of at least 1.2 mm (dry layer thickness min. 1 mm). A protective layer with slip membrane (e.g. fleece laminated dimpled sheet) should be provided on the construction as protection against damage after drying.

Application temperature/climate

Do not apply with air, component and/or substrate temperatures below +5 °C and ensure that temperature does not fall below this temperature until the plaster has hardened sufficiently. Furthermore, the temperature should not exceed 30 °C during application.

In order to prevent rapid dehumidification of the fresh plaster by the exposure to direct sunshine (high surface temperatures), and/or strong wind (danger of cracks reduction in strength) suitable protection measures / treatment (e.g. protective nets, keeping moist) are required.

Cleaning

Clean the machines and tools with water immediately after use.

Notes	<p>Renders must be applied according to EN 13914, DIN 18550-1 or alt. DIN 18550-2, DIN 55699, DIN 18345 and DIN 18350 well as the generally recognized building engineering rules and valid guidelines.</p> <p>The mineral finishing plaster offers some protection against algal and fungal growth and has an inhibiting effect due to its natural alkaline formulation. No guarantee can, however, be given for long-term protection against algal and fungal growth. The susceptibility depends on the local and environmental conditions.</p> <p>Heating in rooms should only be put into operation in stages. Rapid dehumidification, e.g. using dehumidifiers should be avoided.</p>
--------------	--

Coatings and linings

Paints

Finishing renders must be fully hardened and dry before paint coats are applied.

An additional coating in the plaster colour shade with Siliconharz-EG-Farbe paint or MineralAktiv Fassadenfarbe paint is recommended for exterior applications after a drying time of at least 7 days when pigmented plasters are used (for WARM WALL systems with white finishing plasters also) (refer to the Code of Practice “Egalisationsanstriche auf Edelputzen” of the Verband für Dämmsysteme, Putz und Mörtel e.V. (VDPM) (German only). In case of white finishing renders which are to be pigmented in exteriors, a double coat of Knauf Fassadenfarbe façade paint is recommended. At a luminosity < 20, a reflection-optimized paint coat using Fassadol TSR or Autol TSR should be applied to the white finish coat.

In interiors, white finishing coats can be painted and pigmented finishing coats should be painted using Knauf interiors paints.

Notes	<p>When mineral finishing plasters are applied, it is possible that a uniform colour hue may not be achieved or a difference in the degree of gloss may occur on the plaster surface due to processing, consistence, weather-related or drying condition factors.</p> <p>These features, however, in no way impair quality and shall not provide any justification for claims in respect of the material as they stem from uncontrollable physical conditions at the site and they can be equalized by application of a coating.</p> <p>A 100% colour uniformity between the finishing render and the coating as well as on the Knauf colour shade selector card cannot be guaranteed. The colour effect is influenced by lighting effects on the surface, exposure to weather and drying conditions. We recommend that you create some test areas to determine the exact colour effect.</p>
--------------	--

Technical data

Description	Standard	Unit	Noblo
Reaction to fire	EN 13501-1	Category	A1
Graining	–	mm	1.5 / 2.0 / 3.0
Compressive strength	EN 1015–11	Category	CS II
Water vapour diffusion resistance μ	EN 1015-19	–	≤ 20
Thermal conductivity $\lambda_{10, \text{dry, mat}}$ at P = 50 % P = 90 %	EN 1745	W/(m·K) W/(m·K)	≤ 0.82 ≤ 0.89
Capillary water absorption	EN 1015-18	Category	$W_c 2$

The stated technical data were evaluated acc. to the respective test standards. Deviations under site conditions are possible.

Material requirement and efficiency

Graining mm	Coat thickness mm	Consumption approx. kg/m ²	Yield approx. m ² /bag
1.5	1.5	2.3	10.9
2.0	2.0	2.8	8.9
3.0	3.0	3.4	7.4

The consumption values were determined under laboratory conditions. Additional consumption resulting from conditions in practice must be taken into account. The material consumption depends on the roughness, evenness and absorption properties of the substrate as well as the machinery used.

Product range

Noblo	Application	Packaging unit	Material number	EAN
1.5	25 kg	42 bags / pallet	00741432	4003950140679
	25 kg pigmented		00741433	4003950140709
2.0	25 kg		00741435	4003950140730
	25 kg pigmented		00741434	4003950140761
3.0	25 kg		00741436	4003950140792
	25 kg pigmented		00741438	4003950140822

Please refer to the Farbcenter (for possible colour shades at:

knauf-farbcenter.de



Observe safety data sheet!

For safety data sheets and CE marking see
pd.knauf.de



Videos for Knauf systems and products can be found under the following link:
youtube.com/knauf



The Knauf Infothek App now provides all the current information and documents from Knauf Gips KG at any time and in every location in a clear and comfortable way.

knauf.de/infothek

Knauf Direct

Technical Advisory Service:

knauf-direkt@knauf.com

www.knauf.de

Knauf Gips KG Am Bahnhof 7, 97346 Iphofen, Germany

All technical changes reserved. Only the current printed instructions are valid. The stated information represents current state-of-the-art Knauf technology. The entire state of approved engineering rules, appropriate standards, guidelines, and rules of craftsmanship are not included herewith. These and all application instructions have to be adhered to separately by the installer. Our warranty is expressly limited to our products in flawless condition. All application quantities and delivery amounts are based on empirical data that are not easily transferable to other deviating areas.

All rights reserved. All amendments, reprints and photocopies, including those of excerpts, require our expressed permission.