



AMF THERMATEX® Alpha Colour



- AMF THERMATEX® Alpha Color pruža moderan izgled i optimalno je rješenje za prostore koji zahtijevaju izvanrednu apsorpciju zvuka. Uz krem, crnu i srebrnu, akustični asortiman dostupan je i u bojama granita, čelika, zelenog mramora, bakra, hrasta, mesinga, pješčenjaka i betona Vario Design
- Izvrsna apsorpcija zvuka (0.95 α_w)
- Idealno rješenje za uredske prostore, restorane, diskoteke, učionice i obrazovne ustanove



Detalji rubova Ostali detalji rubova na upit	Board 																					
Debljina (mm)	19																					
Dimenzije (mm) Ostali formati na upit	600 x 600 1200 x 600 610 x 610 1220 x 610 625 x 625 1250 x 625																					
Sustav	Vidljiva konstrukcija, demontažni - sustav C																					
Težina	3.3 kg / m ²																					
Boja Ostale boje na upit	Vario Design boje 																					
Aposrpcija zvuka	EN ISO 354 $\alpha_w = 1.00$ prema EN ISO 11654 - Klasa A (crna) $\alpha_w = 0.95$ prema EN ISO 11654 - Klasa A (ostale boje) <table border="1"> <thead> <tr> <th>Frekvencija f (Hz)</th> <th>125</th> <th>250</th> <th>500</th> <th>1000</th> <th>2000</th> <th>4000</th> </tr> </thead> <tbody> <tr> <td>α_p Crna</td> <td>0.45</td> <td>0.80</td> <td>0.95</td> <td>0.95</td> <td>1.00</td> <td>1.00</td> </tr> <tr> <td>α_p Ostale boje</td> <td>0.50</td> <td>0.80</td> <td>0.90</td> <td>0.90</td> <td>1.00</td> <td>1.00</td> </tr> </tbody> </table> NRC = 0.90 prema ASTM C 423	Frekvencija f (Hz)	125	250	500	1000	2000	4000	α_p Crna	0.45	0.80	0.95	0.95	1.00	1.00	α_p Ostale boje	0.50	0.80	0.90	0.90	1.00	1.00
Frekvencija f (Hz)	125	250	500	1000	2000	4000																
α_p Crna	0.45	0.80	0.95	0.95	1.00	1.00																
α_p Ostale boje	0.50	0.80	0.90	0.90	1.00	1.00																
Uzdužna zvučna izolacija	EN ISO 10848-2 $D_{n,f,w} = 28$ dB prema EN ISO 717-1 CAC = 29 dB prema ASTM E 413-10																					
Zvučna izolacija	EN ISO 10140-2 $R_w = 14$ dB prema EN ISO 717-1																					
Reakcija na požar	Euroclass A2-s1, d0 prema EN 13501-1 RUS KM1 (G1, V1, D1, T1) prema 123-FZ																					
Toplinska provodljivost	$\lambda = 0.040$ W/mk prema EN 12667																					
Propusnost zraka	PM1 (≤ 30 m ³ /hm ²) prema DIN 18177																					
Otpornost na vlagu	95% RH																					
Kvaliteta zraka																						
Čišćenje																						
Održavanje	43% www.blauer-engel.de/uz132																					

Options with this icon are available from our **Vario Design** range.
 Products may vary from country to country. Please contact your local sales representative.
 For further information and legal notice, please visit our website.
knaufceilingsolutions.com