

KNAUF

CE

KNAUF CYPRUS LTD
ΧΡΙΣΤΟΥ ΖΕΙΠΕΚΚΗ 1
4504 ΒΑΣΑ ΚΕΛΛΑΚΙΟΥ

10

SK 10:12/03/2014
PILOMAX

CYS EN 998-1:2016

**Κονιάμα τοιχοποιίας γενικής χρήσης για εσωτερικές
και εξωτερικές εφαρμογές CSIV**

Κλάση πυραντίστασης

A1

Πρόσφυση

0.2N/mm² FP:A

Αντοχή σε θλίψη

CSIV

Υδατοαπορρόφηση

W0

Διαπερατότητα υδρατμών

μ25

Θερμική αγωγιμότητα

0,83 W/m·K for P = 50% 0,93 W/m·K for P = 90% (τιμή από πίνακες)

Ανθεκτικότητα

Αξιολόγηση που βασίζεται στην διάταξη που ισχύουν στον προοριζόμενο τόπο χρήσης του επιχρίσματος

KNAUF

CE

KNAUF CYPRUS LTD
CHRISTOY ZEIPEKKI 1
4504 VASA KELLAKIOY

10

SK 10:12/03/2014
PILOMAX

CYS EN 998-1:2016

**General purpose rendering / plastering mortar (GP) for
external and internal application – CS IV**

Reaction to fire	A1
Adhesion	$\geq 0.1 \text{ N/mm}^2$ FP:A
Compressive strength	CS IV
Water absorption	W0
Water vapour diffusion coeff	$\mu 25$
Thermal conductivity	0,83 W/m·K for P = 50% 0,93 W/m·K for P = 90% (tab. mean value)
Durability (against freeze / thaw)	Evaluation based on provisions valid in the intended place of use of the mortar