


VARIOLINE Symetra

















Build on us.


VARIOLINE Symetra is a fleece-coated, acoustic mineral tile that provides up to Class A sound absorption

- Available in a wide range of edge details to suit all design and installation needs
- Provides design flexibility with five printed perforated surface patterns to choose from
- Ideal for offices, foyers and retail spaces


VARIOLINE Symetra

Characteristic	Detailed information							
Edge details 	VARIOLINE Symetra (Alpha)			VARIOLINE Symetra (dB)	VARIOLINE Symetra (Acoustic)	VARIOLINE Symetra (HD)		
	Board	Tegular 24/90	Tegular 15/90	Vector	SL2	Finesse		
Thickness (mm) 	19	19	19	24	19	19		
Dimensions (mm) 	600 x 600 625 x 625 1200 x 600 1250 x 625	600 x 600 625 x 625 1200 x 600	600 x 600 1200 x 600	600 x 600 625 x 625 1200 x 600	On Request	600 x 600 625 x 625 1200 x 600 1250 x 625		
System 	Exposed demountable - System C			Semi-concealed tiles, demountable - System C	Semi-concealed planks, demountable - System I.3 (Bandraster - System I.2 / Corridor - System F.2)	Concealed, demountable - System A.2 / A.3		
Weight 	3.3 kg/m² (Board, Tegular 24/90, Tegular 15/90) 5.0 kg/m² (SL2) 5.2 kg/m² (Finesse) 8.6 kg/m² (Vector)							
Colour & design 	White, with printed patterns Rg 2.5-10, Rg 4-10, Rg 4-16, Rg 4-16 / 4x4, RS 15-20							
Sound absorption 	EN ISO 354		$\alpha_w = 0.95$ (Board, Tegular 24/90, Tegular 15/90) as per EN ISO 11654 - Class A					
			$\alpha_w = 0.65$ (H) (Vector, SL2) as per EN ISO 11654 - Class C					
			$\alpha_w = 0.90$ (Finesse) as per EN ISO 11654 - Class A					
	Frequency f (Hz)		125	250	500	1000	2000	4000
	α_p , Board, Tegular 24/90, Tegular 15/90		0.50	0.80	0.90	0.90	1.00	1.00
	α_p , Vector		0.45	0.40	0.60	0.80	0.95	1.00
α_p , SL2		0.50	0.45	0.60	0.85	0.95	0.95	
α_p , Finesse		0.50	0.70	0.80	0.90	1.00	1.00	
NRC = 0.90 (Board, Tegular 24/90, Tegular 15/90) as per ASTM C 423								
NRC = 0.70 (Vector, SL2) as per ASTM C 423								
NRC = 0.85 (Finesse) as per ASTM C 423								
Sound attenuation 	$D_{n,f,w} = 28$ dB (Board, Tegular 24/90, Tegular 15/90) as per EN ISO 717-1			$CAC = 29$ dB (Board, Tegular 24/90, Tegular 15/90) as per ASTM E 413-10				
	$D_{n,f,w} = 34$ dB (Finesse) as per EN ISO 717-1			$CAC = 35$ dB (Finesse) as per ASTM E 413-10				
	$D_{n,f,w} = 38$ dB (Vector) as per EN ISO 717-1			$CAC = 39$ dB (Vector) as per ASTM E 413-10				
	$D_{n,f,w} = 40$ dB (SL2) as per EN ISO 717-1							
Fire reaction 	Euroclass A2-s1, d0 as per EN 13501-1							
Thermal conductivity 	$\lambda = 0.040$ W/mk (Board, Tegular 24/90, Tegular 15/90) as per EN 12667							
	$\lambda = 0.075$ W/mk (Vector) as per EN 12667							
	$\lambda = 0.060$ W/mk (SL2, Finesse) as per EN 12667							
Air permeability 	PM1 (≤ 30 m ³ /hm ²) as per DIN 18177							
Humidity resistance 	95% RH							
Indoor air quality 	 A+							


Rg 2.5-10




Rg 4-10



Rg 4-16



Rg 4-16 / 4x4



RS 15-20

