



K-Sentials

IC019.de

Product Data Sheet

2020-03

Durhydrit M WoF

High-quality K-Sentials flowing screed compound on the basis of thermal anhydrite

Product description

High-quality K-Sentials flowing screed compound on a thermal anhydrite basis without superplasticizing admixture for manufacturing calcium sulphate flowing screed with a mobile mixer and as factory-mixed dry mortar.

Mixer technology	Graining
Mobile mixer	0 to 8 mm
Factory-mixed dry mortar,	0 to 4 mm

Compound technical data

Compound technical data	Unit	Value
Classification acc. to EN 13454	–	CAB 30
pH value	–	≥ 7
Bulk density (bulk)	g/l	approx. 1150 – 1190

Technical data for a screed mix

Screed mix technical data	Unit	Value
Compressive strength following EN 13813	N/mm ²	≥ 25 (after 28 days)
Bending tensile strength following EN 13813	N/mm ²	≥ 5 (after 28 days)
Water / solid content ratio	–	approx. 0.15
Slump flow (Häggermann funnel) with the addition of a suitable superplasticizing admixture	mm	approx. 230 – 240
Initial setting time	min	approx. 70 (binder)
Application/mortar temperature	°C	5 – 25
Walkable after	h	approx. 24
Heatable after	d	7
Surface hardness	–	No grinding ¹⁾

1) No product-specific grinding required, but does not apply to sanding (cleaning process) of the screed surface directly before the top cover is applied

The above mentioned defined technical characteristics apply for a floor screed mortar mixture following EN 13454-2 consisting of:

33 % Durhydrit M WoF and 67 % standard sand (CEN standard sand EN 196-1) and the addition of an appropriate quantity of suitable superplasticizing admixture.

The strength is influenced, in particular, by the quantity of binder used, the ratio between water and solid content and the quality of the sand.

The examples listed does not replace the requirement for due diligence (obligation to test) in every individual application case by the user/customer.

Order information

Order information	Material no.
Bulk	535060

Knauf Direkt

Technical Advisory Service:

▶ knauf-direkt@knauf.de

▶ www.k-sentials.de

Knauf Gips KG Am Bahnhof 7, 97346 Iphofen, Germany

All technical changes reserved. Only the current printed instructions are valid. The stated information represents current state-of-the-art Knauf technology. The entire state of approved engineering rules, appropriate standards, guidelines, and rules of craftsmanship are not included herewith. These and all application instructions have to be adhered to separately by the installer. Our warranty is expressly limited to our products in flawless condition. All application quantities and delivery amounts are based on empirical data that are not easily transferable to other deviating areas.

All rights reserved. All amendments, reprints and photocopies, including those of excerpts, require our expressed permission..

All given data are reference values with tolerance due to source and production.

Determination method according to Knauf test procedure, can be asked for, if required.

K | SENTIALS