




**KNAUF**CEILING  
Solutions





























## TEHNIČKI LIST

# Antaris C



- Antaris C ploče su napravljene od nove generacije biorazgradive mineralne vune, gline i škroba te posjeduju odlična svojstva u pogledu zaštite od požara. Glatka bijela laminirana završna obrada nudi visoki nivo apsorpcije zvuka za bolji akustički komfor.

- Dobra apsorpcija zvuka (0.70  $\alpha_w$ )
- Visoka nivo refleksije svetlosti (86%)
- ISO 5
- Idealno rješenje za maloprodajne objekte, urede, sale za sastanke, tehničke prostorije i proizvodne objekte.

<b>Detalji rubova</b> Ostali detalji rubova na upit		Board 	Tegular 24 	Tegular 15 														
<b>Debljina (mm)</b>		13	13	13														
<b>Dimenzije (mm)</b> Ostali formati na upit		600 x 600 1200 x 600	600 x 600	600 x 600														
<b>Sustav</b>		Vidljiva konstrukcija, demontažni - sustav C																
<b>Težina</b>		3.0 kg / m <sup>2</sup>																
<b>Boja</b>		 Bijela																
<b>Aposrpcija zvuka</b>		EN ISO 354 $\alpha_w = 0.70$ prema EN ISO 11654 - <b>Class C</b> <table border="1"> <tr> <td>Frekvencija f (Hz)</td> <td>125</td> <td>250</td> <td>500</td> <td>1000</td> <td>2000</td> <td>4000</td> </tr> <tr> <td><math>\alpha_p</math></td> <td>0.40</td> <td>0.55</td> <td>0.60</td> <td>0.75</td> <td>0.95</td> <td>1.00</td> </tr> </table> NRC = <b>0.70</b> prema ASTM C 423			Frekvencija f (Hz)	125	250	500	1000	2000	4000	$\alpha_p$	0.40	0.55	0.60	0.75	0.95	1.00
Frekvencija f (Hz)	125	250	500	1000	2000	4000												
$\alpha_p$	0.40	0.55	0.60	0.75	0.95	1.00												
<b>Uzdužna zvučna izolacija</b>		EN ISO 10848-2 $D_{n,f,w} = 30$ dB prema EN ISO 717-1 CAC = <b>30 dB</b> prema ASTM E 413-10																
<b>Zvučna izolacija</b>		EN ISO 10140-2 $R_w = 18$ dB prema EN ISO 717-1																
<b>Reakcija na požar</b>		Euroclass <b>A2-s1, d0</b> prema EN 13501-1																
<b>Refleksija svjetlosti</b>		<b>86%</b>																
<b>Toplinska provodljivost</b>		$\lambda = 0.060$ W/mk prema EN 12667																
<b>Otpornost na vlagu</b>		<b>90% RH</b>																
<b>Razred čistoće prostora</b>		<b>ISO 5</b> prema EN ISO 14644-1																
<b>Kvaliteta zraka</b>		 A+	 E1															
<b>Čišćenje</b>																		
<b>Održavanje</b>				 <a href="http://www.blauer-engel.de/uz132">www.blauer-engel.de/uz132</a>														

Proizvodi se mogu razlikovati između prodajnih područja. Molimo kontaktirajte svog lokalnog prodajnog predstavnika. Za dodatne i pravne informacije posjetite našu web stranicu.