

AQUAPANEL® Q4 Finish

Technical Data Sheet 12/2023



Aquapanel® Q4 Finish

Finish

Product Description

Water repellent, ready to use finishing render for high quality surfaces, used in Aquapanel interior applications.

Storage

- Buckets should be kept unopened in a dry environment between 5 - 35 °C and should not be exposed to direct sunlight.
- Storage life is only valid for unopened buckets.
- Unused buckets should be kept unopened.
- Buckets should be kept in frost-free conditions.

Standards referred to

DIN 18550, Type P II
EN 998 - 1, CS II

Fields of Application

- Aquapanel® Indoor panel surfaces
- Aquapanel® Universal indoor panel surfaces

General Data

Description	Weight (kg)	Packaging (pcs/pallet)	Shelf Life	Material Number
Aquapanel® Q4 Finish	20	1	12 ay	82637

Technical Data

Description	
Color	White
Density (kg / L)	1,6
Reaction to fire	A2-s1, d0
Open time	>25 minutes (at 23°C and 63°C rel. humidity)
Drying time	approx. 24 hours (at 23°C and 63°C rel. humidity)
Max. grain size	50 µm
Viscosity	29-31 Pa.s
Working temperature	>5°C

Material Comsumption

Product	Unit	Consumption kg/m ²
Aquapanel® Q4 Finish (for 1 mm coating thickness)	kg	approx. 1,7

System Performance Values

Performance values as sound insulation, fire resistance etc. may differ acc. to the drywall system to be applied. Please check the performance values of the drywall systems;

[Knauf Technical Website](#)
[Document Center](#)

Application

Application should be done acc. to the applicable standards (TS 1475) and acc. to the Knauf Technical Brochures of the respective drywall system.

▶ 444 YAPI - 9274

▶ www.knauf.com.tr / www.teknik.knauf.com.tr

▶ teknik@knauf.com

Center: Knauf Moment Beştepe Office, Beştepe Mah. 32.Cadde No:1/212-218 06560 Beştepe-Yenimahalle
/ ANKARA Tel: 0312 297 0100 Faks: 0312 266 4506