

KNAUF

K Joint 120 Gypsum Jointing Compound

120 Minutes formula



Build on us.

K JOINT 120

General Information

Gypsum Jointing Compound; K Joint 120 is produced from high quality gypsum. Used to coat a joints and screw head, also able to fix the fracture on any type of gypsum board.

- 2:1 mixing ratio, 50% more coverage
- A fine mixture provides a smooth application
- Elastic mixture, protects the wall from cracking



Product Information

Pack Size (kg)	Mixing Ratio (Compound : Water)	Setting Time	Coverage	Shelf Life
20	2 parts of compound : 1 part of water	60 minutes	40 sq.m.	6 months*

*Sealed bag



Storing

Tightly close the bag, keep in dry place with temperature less than 50°C, and place it above the ground level. Do not exposed to the moisture or water.

Caution

Do not use the mixture in the temperature that higher than 45°C or lower than 0°C



Instruction



- 1 Mix the compound and water with a ratio of 2:1, leave it for 2 minutes then stir them until there is no lumps left



- 2 Apply the first coat on the joint with small trowel, apply a cotton tape over it and apply another layer of coating, coat the screw head then leave them to dry out for 120 minutes following the setting time.



- 3 Apply another 2 layers of coating with large trowel with 120 minutes interval between each coat. After the coating is completely dry, polish with sand paper then clean the surface before apply a paint.





The Siam Gypsum Industry (Saraburi) Co., Ltd.
Pakin Building, 5th floor, 9 Ratchadapisek Road,
Dindang, Bangkok 10400

☎ +66 2 555 0015

✉ marketingknaufgypsumthailand@knauf.com

🌐 www.knauf.com

📍 Knauf Thailand

