



Jan 2021

Factory Clad 41

For metal clad roofs and walls

Description

Factory Clad 41 with ECOSE® Technology is a resilient, flexible unfaced blanket insulation made from Glasswool bonded by thermosetting resin providing a thermal conductivity of 0.041 W/m.K. The blanket is suitable for application of facings and has sufficient tensile and bond strength for normal handling by the laminator and contractor. Faced with a vapor retarder, it can be installed in exterior wall surfaces of pre-engineered buildings.

Application

FactoryClad 41 are used for the thermal and acoustic insulation of roofs in profiled metal clad buildings and portable buildings. FactoryClad 41 are manufactured 1200mm wide to suit commonly used rail and bracket systems and in long lengths, making them particularly suitable for use in twin skin profiled metal cladding systems and standing seam roofs.

Standards

FactoryClad 41 is manufactured in accordance with BS EN 13162, OHSAS 18001 Occupational Health and Safety Management Systems, ISO 14001 Environmental Management Systems, and ISO 9001 Quality Management Systems, as certified by Bureau Veritas.

Performance

Thermal

FactoryClad 41 have a thermal conductivity of 0.041 W/mK at 25 C

Fire

FactoryClad 41 Wall does not exceed 25 Flame Spread, 50 Smoke Developed when tested in accordance with ASTM E84. (UF)

FactoryClad 41 Wall does not exceed 25 Flame Spread, 50 Smoke Developed when tested in accordance with ASTM E84. (WMP 10)

Benefits

- Exceptionally high tear strength
- Provides thermal and acoustic performance
- Cost effective
- Lightweight, easy to handle and install

Factory Clad 41

Durability

FactoryClad 41 is odourless, rot proof, non-hygroscopic, does not sustain vermin and will not encourage the growth of fungi, mould or bacteria.

Certification

FactoryClad 41 are certified under UL 723, DCL Product Conformity, EUCEB for conformity of fibres produced with the requirements of Note Q of the Regulation (EC) No 1272.2008 of EP and EC, EUROFINS Indoor Air Quality Gold.

Environmental

FactoryClad 41 represents no known threat to the environment and has zero Ozone Depletion Potential and zero Global Warming Potential.

Water Vapor Permeance

Factory Clad 41 (FSK) have a maximum water vapor permeance of 0.02 perms as per ASTM E96, Procedure A.

Factory Clad 41 (WMP10) have a maximum water vapor permeance of 0.02 perms as per ASTM E96, Procedure A.

Handling and storage

FactoryClad 41 is easy to handle and install, being lightweight and easily cut to size, where necessary. It is supplied enclosed in polythene which is designed for short term protection only. For longer term protection on site, the product should be stored either indoors, or under cover and off the ground. FactoryClad 41 should not be left permanently exposed to the elements.

Facing	Thickness	Length	Width	Area per pack	Thermal Conductivity	R Value	Density	No.Rolls
	(mm)	(m)	(mm)	(m ²)	(W/m.K)	(m ² .K/W)	(kg/m ³)	in pack
FSK	100	20	1200	24	0.041	2.43	12	1
FSK	50	20	1200	24	0.041	1.22	12	1

All dimensions are nominal

Knauf Insulation mineral wool products made with ECOSE® Technology benefit from a no added formaldehyde binder, which is up to 70% less energy intensive than traditional binders and is made from rapidly renewable bio-based materials instead of petroleum-based chemicals. The technology has been developed for Knauf Insulation's glass and rock mineral wool products, enhancing their environmental credentials without affecting the thermal, acoustic or fire performance. Insulation products made with ECOSE Technology contain no dye or artificial colours.

Knauf Exeed Insulation LLC

Mussaffah ICAD 1,
P.O.Box 34332,
Abu Dhabi,
United Arab Emirates

Customer Service (sales)

Tel: +971 2 551 2453

Technical Support & Marketing

Tel: +971 2 551 2453

Email: technicalsupport@kei.ae