

KNAUF



FINISH BORA

Interior Plaster Data Sheet

02/2021

Knauf Interior Skimming Compound - Finish Bora

Manufactured from crushed dolomite, then mixed together with polymer and organic binders.



Knauf Interior Skimming Compound - Finish Bora



Properties	Technical aspects
<ul style="list-style-type: none"> • Easy to apply • Easy to sand • Mix only with water even on 2nd coat • Over 12 hrs in the bucket • Good adhesion / bonding to wall • Satin/smooth & white finish 	<ul style="list-style-type: none"> • Mixing ratio powder : water (25kg:15 l) or (1kg:0.6 l) • 1mm Skimming per coat • 24hrs to dry after one coat • Sanding of P180 • European tested (CE) under norm EN13963
Application	Product Information
<ul style="list-style-type: none"> • Skimming gypsum boards - interior • Skimming cement plastered walls - interior 	<ul style="list-style-type: none"> • Drying time per coat: 24 hours • Coverage 1 kg per m² • Available in 25 kgs • 9 months from the manufacturing date

Storage
Protect against high temperatures and exposure to direct sunlight. Can be stored for up to 12 months at room temperature.

Please contact our sales department for inquiries about storage and packing.

Knauf Gypsum Tanzania Ltd

▶ Plot 17 Block 186030,
14110 Mwindu Lane off Kinondoni Rd,
Dar Es Salaam, Tanzania

▶ Technical service: +255 752 599 644

▶ Landline: +255 222 162 930

▶ technicalsupport@knauf.co.tz

www.**KNAUF**.co.tz

The information provided in this leaflet is only intended to give guidance in selecting and using Knauf products. While we make every effort to ensure its accuracy, neither Knauf Gypsum Tanzania Limited and its branches nor any of its employees or affiliates warrant or assume any legal liability or responsibility for the completeness or usefulness of any failure in installation or constructing structure installation or building or caused by using this leaflet. Readers are advised to independently verify this information prior to rely on it. In particular, readers must obtain appropriate independent advice on the use of products in specific structures, installations or buildings to ensure compliance with all regulations, including health and safety regulations. Knauf reserves the right to amend technical specifications without notice.

The constructional and structural properties and characteristic building physics of Knauf system can solely be ensured with the exclusive use of Knauf system components, or other products expressly recommended by Knauf.